

RECEIVED  
CENTRAL FAX CENTER

MAY 09 2008

PATENT  
P56964**IN THE CLAIMS**

Pursuant to 37 CFR §121(c), the claim listing, including the text of the claims, will serve to replace all prior versions of the claims, in the application.

Please cancel claims 1 thru 11, 13, 14, 19 and 20 without prejudice or disclaimer, and amend claims 12 and 18 as follows:

Claims 1 - 11. (Canceled)

12. (Currently Amended/Withdrawn) A method for fabricating an organic electroluminescent display, comprising the steps of:

disposing first anodes of red, green and blue unit pixels on a substrate;

forming an anode electrode of the red unit pixel by disposing a second anode of the [[R]] red unit pixel on the first anode of the red unit pixel, each anode electrode of the red unit pixel including a first film having a high reflectivity and a second film for adjusting a work function;

forming anode electrodes of the green and blue unit pixels by disposing second anodes of the green and blue unit pixels on the first anodes of the green and blue unit pixels, respectively, each anode electrode of the green and blue unit pixels including a first film having a high reflectivity and a second film for adjusting a work function;

disposing respective organic thin-film layers on the anode electrodes of the red, green and blue unit pixels; and

disposing a cathode electrode over an entire surface of the substrate[[,]];

wherein the second anode of at least one unit pixel of the red, green and blue unit pixels has a thickness different from thicknesses of the second anodes of other unit pixels of the red, green and blue unit pixels; and

wherein a thickness of the second film of the red unit pixel is in a range of one of

PATENT  
P56964

19 250 to 450Å and 700 to 750Å, a thickness of the second film of the green unit pixel is in a  
20 range of one of 50 to 150Å and 200 to 300Å, and a thickness of the second film of the B  
21 unit pixel is in a range of 50 to 150Å.

Claims 13-14. (Canceled)

1 15. (Previously Presented) A method for fabricating an organic  
2 electroluminescent display, comprising the steps of:

3 disposing sequentially a first anode electrode material and a second anode  
4 electrode material of red, green and blue unit pixels on a substrate;

5 etching the first and second anode electrode materials to form anode electrodes of  
6 the red, green and blue unit pixels, each of the anode electrodes of the red, green and blue  
7 unit pixels including a first film having a high reflectivity and forming a first anode and a  
8 second film for adjusting a work function and forming a second anode;

9 disposing respective organic thin-film layers on the anode electrodes of the red,  
10 green and blue unit pixels; and

11 disposing a cathode electrode over an entire surface of the substrate;

12 wherein the second anode of at least one unit pixel of the red, green and blue unit  
13 pixels has a thickness different from thicknesses of the second anodes of other unit pixels  
14 of the red, green and blue unit pixels;

15 wherein the first and the second anode electrode materials are patterned by using  
16 photosensitive film patterns having thicknesses different from each other, depending  
17 upon the red, green and blue unit pixels; and

18 wherein a thickness of the second anode of the red unit pixel is in a range of one of  
19 250 to 450Å and 700 to 750Å, a thickness of the second anode of the green unit pixel is in

PATENT  
P56964

20 a range of one of 50 to 150Å and 200 to 300Å, and a thickness of the second anode of the  
21 blue unit pixel is in a range of 50 to 150Å.

1 16. (Previously Presented) The method according to claim 15, wherein the second  
2 anode of the red unit pixel is thicker than the second anodes of the other unit pixels.

Claim 17. (Canceled)

1 18. (Currently Amended/Withdrawn) A method for fabricating an organic  
2 electroluminescent display, comprising the steps of:  
3 disposing first anodes of red, green and blue unit pixels on a substrate;  
4 disposing a second anode electrode material over an entire surface of the substrate;  
5 etching the second anode electrode material to form respective second anodes on  
6 the first anodes of the R, G and B unit pixels, thereby forming respective anode  
7 electrodes of the red, green and blue unit pixels, each of the anode electrodes of the red,  
8 green and blue unit pixels including a first film having a high reflectivity and a second  
9 film for adjusting a work function;  
10 disposing organic thin-film layers on the respective anode electrodes of the red,  
11 green and blue unit pixels; and  
12 disposing a cathode electrode over an entire surface of the substrate;  
13 wherein a second anode of at least one unit pixel of the red, green and blue unit  
14 pixels has a thickness different from thicknesses of second anodes of [[the]] other unit  
15 pixels of the red, green and blue unit pixels; and  
16 wherein a thickness of the second film of the red unit pixel is in a range of one of  
17 250 to 450Å and 700 to 750Å, a thickness of the second film of the green unit pixel is in a

PATENT  
P56964

18 range of one of 50 to 150Å and 200 to 300Å, and a thickness of the second film of the  
19 blue unit pixel is in a range of 50 to 150Å.

Claims 19-20. (Canceled)

1 21. (Previously Presented) The method according to claim 15, wherein the  
2 photosensitive film patterns are formed by a photo process using a half-tone mask.